

TABLE OF CATALYZATION OF PRESTEC PER QUART

Catalyst to be used: Norox MEKP-9

1. Refer to Prestec by liquid measure as follows:

1 gallon = 8 Pints

1 quart = 32 fluid ounces = $\frac{1}{4}$ gallon

1 Pint = 8 ~ 2oz.

2 quarts = 64 fluid ounces = $\frac{1}{2}$ gallon

1 Pint = 4 ~ 4oz.

3 quarts = 96 fluid ounces = $\frac{3}{4}$ gallon

4 quarts = 128 fluid ounces = 1 gallon

2. To catalyze 1 quart of Prestec

<u>Catalyst % to add</u>	<u>Drops</u>	<u>cc, ml or grams</u>	<u>Ounces</u>
$\frac{1}{2}$	160	5	$\frac{1}{8}$
1	320	10	$\frac{1}{4}$
1 $\frac{1}{2}$	480	15	$\frac{3}{8}$
2	640	20	$\frac{1}{2}$

3. For smaller amounts of Prestec at 2% MEK Peroxide catalyst

<u>Amount of material</u>	<u>Amount of MEK Peroxide at 2%</u>		
	<u>Drops</u>	<u>cc, ml or grams</u>	<u>Ounces</u>
1 fluid ounce	20	$\frac{5}{8}$	$\frac{1}{64}$
2 fluid ounces	40	1 $\frac{1}{4}$	$\frac{1}{32}$
4 fluid ounces	80	2 $\frac{1}{2}$	$\frac{1}{16}$
8 fluid ounces – $\frac{1}{2}$ pint	160	5	$\frac{1}{8}$
16 fluid ounces – 1 pint	320	10	$\frac{1}{4}$
32 fluid ounces – 1 quart	640	20	$\frac{1}{2}$
1 cc = 40 drops	$\frac{1}{4}$ teaspoon = 1 cc	20 cc = $\frac{1}{2}$ oz	

Simtec Coatings ~ 2088 2nd Street, Norco, CA 92860 ~ 951-279-7010-Direct

Email: simteccoatings@att.net